

OEKOSTRETCH

SPORT
SPORT BLOCK

MODE D'EMPLOI

Lavage 60°C max

	Température	150-160 °C
	Temps de pose.....	9 à 12 secondes
	Pression.....	moyenne (2-3 bars)
	Démoulage.....	à froid ou tiède

Ces valeurs sont données à titre indicatif : effectuer toujours des tests avant de lancer une production.

L'oekestretch n'adhère pas sur les fibres nylon fortement imperméabilisées .

CONSEILS

- Repassage possible en mode délicat
- Tendre les vêtements pour éviter les faux plis et les surépaisseurs (boutons,bas de maillots, coutures de manches, cols, autres logos...)
- Enfiler les vêtements dans les jeannettes
- Fibre nouvelle : procéder à des essais ou nous consulter
- Nettoyage à sec : non recommandé

monblason


Heat transfer solutions / Since 1906

OEKOSTRETCH

SPORT
SPORT BLOCK

INSTRUCTIONS

Washable up to 60°C

	Temperature	150-160 °C
	Pressing time.....	9 à 12 seconds
	Pressure.....	middle (2-3 bars)
	Peeling.....	cold or lukewarm

These settings are given for guidance : always give a try before strating a production.
Oekostretch does not stick on strongly waterproof nylon.

ADVICES

- Can be ironed in delicate mode
- Correctly stretch the garment to avoid folds and thicknesses (mind buttons, tee-shirt edges, sleeve sewings, neckband, other logos...)
- Slip on the garment using the press table
- Unknown fiber : do a test or contact us
- Dry cleaning is not recommended

www.monblason.com

